RG104 E-1 Box 121

WEEKLY REPORT OF GOLD DEPOSITS MELTED AT UNITED STATES MINT.

1880

Date.	Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.	Gain. Oz.	Dec.	Description of Bullion.
March 29th	555	G. C. Thompson	17	10	15	31	1	89	11 12			Jewelry
	6	W. H. Lee	57	33	57	32		01	02			Bar
	7	A. Losse	6	15	5	99		16	2 67			D.Pl. & Fillings
	8	A. Pike	7	77	7	75		02	25			Button
	9	Morgan & Headly	7	86	7	85		01	12			Bars
	60	A. London Snowden, Supt.	124	92	124	90		02	02			Bars, U.S. M. N.C.
	1	Hastings & Co.	134	30	134	30						U.S. Coin
30th	2	G. C. Thompson	9	48	9	48						Button, Geo.
	3	Do	27	55	24	93	2	62	9 36			Jewelry, Watch Cases & Scraps.
	4	Do	11	05	10	09		96	8 73			Ring, Bar
	5	John Stuerty	8	55	8	39		16	1 67			Button
	6	A. Naas	16	64	15	89		75	4 41			Chains
	7	Morgan & Hastings	53	73	53	73						U.S. Coin
31st	8	G. C. Thompson	4	06	4	03		03	75			Button, Col.
	9	Do	11	52	11	33		19	1 58			Button
	70	I. C. White	13	17	12	77		40	3 07			Fillings & D.Pl.
	1	C. & A. Pequignot	73	03	72	98		05	06			Bar
April 1st	2	G. C. Thompson	8	71	8	46		25	2 67			Aml & Grs, S.C.
	3	Do	6	47	6	25		22	3 67			Aml & Grs, N.C.
	4	Do	42	73	37	50	5	23	12 15			Ring, Base
	5	A. Losse	6	92	6	76		16	2 29			D.Pl., Fillings & Filings
	6	G. C. Thompson	130	90	92	63	38	27	29 21			Rings, Base
	7	Chas. V. Jones	23	69	18	92	4	77	19 87			Leaf
	8	W. H. Sheafer & Co.	84	80	69	33	15	47	18 20			Rings, Base
	9	H. Stait	18	25	18	23		02	11			Bar
2nd	80	G. C. Thompson	2	98	2	93		05	1 67			Button & Pieces, Geo.
	1	A. R. Martin	45	25	45	29					04	Bar
	2	Hastings & Co.	134	32	134	32						U.S. Coin
	3	Morgan, Hastings & Co.	53	72	53	72						U.S. Coin
	4	G. C. Thompson	19	90	13	97	5	93	29 65			Ring, Base
	5	Do	16	10	11	28	4	82	30 12			Jewelry
	6	Phillips & Jacobs	53	74	53	74						U.S. Coin
3d	7	H. Muhr's Sons	15	04	15	04						Bars
	8	G. C. Thompson	10	56	10	25		31	2 82			Jewelry & Watch Cases
	9	Do	48	56	48	30		26	53			Buttons, Dakota
	90	Do	6	98	6	79		19	2 71			Bar, Watch Case, &c.
	1	Simons, Bro. & Co.	104	30	104	15		15	15			Bars
	2	Richd. Nelms	53	73	53	73						U.S. Coin
	3	Geo. H. Smith	12	66	12	06		60	4 62			Aml, N.C.
	4	A. London Snowden, Supt.	79	83	79	81		02	02			Bars, U.S. Mint, N.C.
			1564	35	1480	40	83	99	7 95		04	

Notes of Melter and Refiner.

15 Ap/80.

The deposits are from the following sources:

N. Carolina	(2)	4
S. Carolina		1
Georgia	(2)	2
Colorado	(1)	1
Dacotah	(1)	1
Finer bullion	(6)	17
Jewelry, &c.		5
Baser bullion		6
Dental Plate		3
Coin		6
Total		40

The loss in melting the mixt metal from Georgia N. Carol. 4.14 % is reasonable; — from S. Carolina, 2.67 %, is moderate; the finer bullion, 0.15 %, is a good average; — the jewelry &c., 11.56 %, is moderate; — and the baser bullion, 19.63 %, is below the usual average. The loss on dental plate, 2⅔ %, is rather full. No loss on 6 deposits of coin is too low.

Jas. C. Booth, M. & R.

For week ending April 3d, 1880.

Approximate value, $22,946.20

J. Robley Dunglison, Register.

To the Director of the Mint.

RG104 E-1 Box 121

Report of Gold Deposits melted for week ending April 3rd 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending April 3, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]